

## TECHNICAL DATA SHEET

### HIGH BREATHABLE ROOFING MEMBRANE **HURAGAN 150**



**HURAGAN 150** is 4-layers, diffuse-open membrane designed as a layer of initial covering under the external roof covering. Membrane **HURAGAN150** is completely waterproof, protects thermal insulation from the outside against rain or snow from the outside and also it is an excellent wind barrier intended to cover of the building walls in framed structures, as well as in log houses, structures of residential buildings and industrial halls.

The product can be used in all ventilated and unventilated roofs, under a variety of roofing (eg. ceramic tile, concrete tile, metal tiles, etc.).

Characteristics		Test metod	Unit	Declared value
<b>Dimensions</b>	<b>width *</b>	EN 1848-2	m	1,5 ± 0,5%
	<b>length of the the roll *</b>		m	50 (-0/+2%)
<b>Mass per unit area</b>		EN 1849-2	g/m <sup>2</sup>	150 ± 10%
<b>Reaction to fire</b>		EN ISO 11925-2	-	Class E
<b>Watertightness (2 kPa)</b>		EN 1928	-	Class W1
<b>Watertightness after artificial ageing</b>		EN 1296 EN 1928	-	Class W1
<b>Resistance to tearing</b>	<b>in longitudinal direction</b>	EN 12310-1	N	160 (+50; -50)
	<b>in transverse direction</b>		N	170 (+50; -50)
<b>Tensile strength</b>	<b>in longitudinal direction</b>	EN 12311-1	N/50mm	240 (+60; -60)
	<b>in transverse direction</b>		N/50mm	130 (+40; -40)
<b>Elongation</b>	<b>in longitudinal direction</b>		%	90 (+40; -40)
	<b>in transverse direction</b>		%	150 (+50; -50)
<b>Tensile strength after artificial ageing</b>	<b>in longitudinal direction</b>	EN 1296 EN 1297 EN 12311-1	N/50mm	190 (+50; -50)
	<b>in transverse direction</b>		N/50mm	100 (+40; -40)
<b>Elongation after artificial ageing</b>	<b>in longitudinal direction</b>		%	70 (+30; -30)
	<b>in transverse direction</b>		%	120 (+50; -50)
<b>Water vapour transmission S<sub>d</sub></b>		EN ISO 12572	m	0,02 (+0,03; -0,01)
<b>Flexibility at low temperature</b>		EN 1109	°C	-30
<b>Application temperature range</b>		-----	°C	-30 ÷ 80
<b>Dangerous substances</b>		-----	-	NPD

\*or as agreed with the customer

The membrane **is not resistant** to action of the petroleum substances (e.g. oil, gasoline etc.).